

FLUXA BLACK-O

Black Magnetic Powder Suspension

ready for use

Product Description

- Ready-to-use suspension for magnetic particle testing
- Ready to use diluted with FLUXA TEST OIL
- Ideal for serial testing under daylight
- Detection of finest cracks
- Excellent wetting properties

Product Specifications

- Concentration: FLUXA Concentrate BLACK-O 1:100 in FLUXA TEST OIL
- Application temperature: -10 °C to 60 °C
- Average particle size: approx. 1 µm
- Flash point: > 65 °C
- Viscosity (20 °C): 2 mm²/s
- Density (20 °C): approx. 0.8 g/cm³
- Settling volume (1 h): approx. 0.3 to 0.5 ml
- SAE sensitivity: ≥ 6
- Shelf life: 3 years
- Storage temperature: 4 °C to 45 °C

Approvals and Specifications

- Type-tested according to DIN EN ISO 9934-2
- SAE AMS 2641, ASTM E 1444, ASTM E 709, ASME Code Sec. V Art. 7

Your Benefits

- Easy handling
- High resistance
- Ready to use

For the Environment

- Low odour
- Free from hazardous substances



Packaging

- 10 l canister (order no.: 9014.2)
- 25 l canister (order no.: 9014.25)

KARL DEUTSCH Pruef- und Messgeraetebau GmbH + Co KG · Otto-Hausmann-Ring 101 · 42115 Wuppertal · Germany
Phone +49 202 7192 0 · info@karldeutsch.de · www.karldeutsch.de

The Technical Data Sheet provides recommendations and possible examples. Obligations or liability cannot be derived therefrom. The information is based on our current knowledge and does not release the user from personal responsibility. The object conditions and product suitability must be checked professionally and appropriately. Take into account the information given in the Safety Data Sheet. We are happy to provide test samples for trials. Issue: 11 June 2026