

KD-CHECK DD-1

Dry Developer

Product Description

- Dry developer
- Type-tested according to DIN EN ISO 3452-2
- Form a according to DIN EN ISO 3452-2
- Approved according to AMS 2644 (listed on QPL-AMS 2644)
- Suitable for metals and non-metals (suitability for plastics must be checked beforehand)
- Application by dusting (vortex chamber) or with an electrostatic unit

Product Specifications

- Application range: +10 °C to +50 °C
- Corrosive components (fluorine, chlorine + sulphur): < 200 ppm each according to DIN EN ISO 3452-2
- Corrosive components (fluorine, chlorine + sulphur): < 1 % each according to ASME Code
- Shelf life: 5 years
- Storage temperature: 5 °C to 45 °C

Approvals and Specifications

- Low sulphur and halogen content according to DIN EN ISO 3452-2 and ASME Code, Section V, Article 6
- Type-tested according to DIN EN ISO 3452-2
- QPL-AMS 2644 listed

Your Benefits

- Label-free



Packaging

- 1 kg drum (order no.: 9908.1)
- 20 kg drum (order no.: 9908.2)

KARL DEUTSCH Pruef- und Messgeraetebau GmbH + Co KG · Otto-Hausmann-Ring 101 · 42115 Wuppertal · Germany
Phone +49 202 7192 0 · info@karldeutsch.de · www.karldeutsch.de

The Technical Data Sheet provides recommendations and possible examples. Obligations or liability cannot be derived therefrom. The information is based on our current knowledge and does not release the user from personal responsibility. The object conditions and product suitability must be checked professionally and appropriately. Take into account the information given in the Safety Data Sheet. We are happy to provide test samples for trials. Issue: 11 June 2026