

KD-CHECK WDD

Water-Based Wet Developer suspensible

Product Description

- Water-based wet developer, suspensible
- Sample tested according to DIN EN ISO 3452-2
- Form c according to DIN EN ISO 3452-2
- Recommended application concentration: 10 % – 20 % in water
- Suitable for metals and non-metals (suitability for plastics must be checked beforehand)
- Particularly suitable for immersion applications

Product Specifications

- Application temperature: +10 °C to +60 °C
- Corrosive components (fluorine, chlorine + sulphur): < 200 ppm each according to DIN EN ISO 3452-2
- Corrosive components (fluorine, chlorine + sulphur): each < 1 % according to ASME Code
- Shelf life: 5 years
- Storage temperature: 5 °C to 45 °C

Approvals and Specifications

- Low sulphur and halogen content according to DIN EN ISO 3452-2 and ASME Code, Section V, Article 6
- Type-tested according to DIN EN ISO 3452-2

Your Benefits

- White, uniform and high-contrast layer
- Excellent contrast to the penetrant

For the Environment

- Label-free



Packaging

- 1 l bottle (order no.: 9923.1)
- 5 l canister (order no.: 9923.2)
- 10 l canister (order no.: 9923.3)
- 25 l canister (order no.: 9923.6)

KARL DEUTSCH Prüf- und Messgerätebau GmbH + Co KG · Otto-Hausmann-Ring 101 · 42115 Wuppertal · Germany
Phone +49 202 7192 0 · info@karldeutsch.de · www.karldeutsch.de

The Technical Data Sheet provides recommendations and possible examples. Obligations or liability cannot be derived therefrom. The information is based on our current knowledge and does not release the user from personal responsibility. The object conditions and product suitability must be checked professionally and appropriately. Take into account the information given in the Safety Data Sheet. We are happy to provide test samples for trials. Issue: 11 June 2026