## **TECHNICAL DATA SHEET**

# FLUXA HS-0

### Fluorescent Magnetic Particle Suspension

#### Product Description –

- Ready-to-use concentrate for magnetic particle testing
- Ideal for series testing under UV light
- Detection of finest cracks
- Oil-suspendable
- For mixing with FLUXA Test Oil or Test Oil 110

#### **Product Specifications** –

- Recommended concentration: 1:100 to 1:200 in oil.
- Application temperature: -10 °C to 60 °C
- Average particle size: approx. 3 µm
- Fluorescence coefficient: approx. 4 cd/W
- Density (20 °C): approx. 0.9 g/cm<sup>3</sup>
- Settling volume (1 %, 2 h): approx. 0.2 to 0.3 ml
- SAE sensitivity:  $\geq 7$
- 3 years minimum keeping time at room temperature

#### **Approvals and Specifications**

- Type-tested according to DIN EN ISO 9934-2
- SAE AMS 3044, ASTM E 1444, ASTM E 709, ASME Code Sec. V Art. 7, NAVSEA T9074-AS-GIB-010/271

#### Your Benefits

- Easy handling
- High resistance
- Label-free

#### For the Environment

- Low odour
- Free from hazardous substances



#### Packaging -

1 | bottle (order no.: 9314.1)

KARL DEUTSCH Pruef- und Messgeraetebau GmbH + Co KG · Otto-Hausmann-Ring 101 · 42115 Wuppertal · Germany Phone +49 202 7192 0 · Fax +49 202 7192 123 · info@karldeutsch.de · www.karldeutsch.de

The Technical Data Sheet provides recommendations and possible examples. Obligations or liability cannot be derived therefrom. The information is based on our current knowledge and does not release the user from personal responsibility. The object conditions and product suitability must be checked professionally and appropriately. Take into account the information given in the Safety Data Sheet. We are happy to provide test samples for trials. Issue: 14 July 2022

## **KARL DEUTSCH**