

FLUXA HS-0-110

**Fluorescent
Magnetic Particle Suspension**
ready for use

Product Description

- Ready-to-use suspension for magnetic particle testing
- Ready to use diluted with FLUXA Test Oil 110
- Ideal for serial testing under UV light
- Detection of finest cracks
- Excellent wetting properties

Product Specifications

- Concentration: FLUXA Concentrate HS-O 1:100 in FLUXA Test Oil 110
- Application temperature: 10 °C to 100 °C
- Average particle size: approx. 3 µm
- Fluorescence coefficient: approx. 4 cd/W
- Flash point: > 100 °C
- Viscosity (20 °C): 2.6 mm²/s
- Viscosity (38 °C): 3.8 mm²/s
- Density (20 °C): approx. 0.8 g/cm³
- Settling volume (2 h): approx. 0.2 ml
- SAE sensitivity: ≥ 7
- 3 years minimum keeping time at room temperature

Approvals and Specifications

- Type-tested according to DIN EN ISO 9934-2
- SAE AMS 2641, SAE AMS 3044, SAE AMS 3045, ASTM E 1444, ASTM E 709, ASME Code Sec. V Art. 7, NAVSEA T9074-AS-GIB-010/271

Your Benefits

- Easy handling
- High resistance
- Ready-to-use

For the Environment

- Low odour
- Free from hazardous substances



Packaging

- 10 l canister (order no.: 9315.2)

KARL DEUTSCH Prüf- und Messgerätebau GmbH + Co KG · Otto-Hausmann-Ring 101 · 42115 Wuppertal · Germany
Phone +49 202 7192 0 · Fax +49 202 7192 123 · info@karldeutsch.de · www.karldeutsch.de

The Technical Data Sheet provides recommendations and possible examples. Obligations or liability cannot be derived therefrom. The information is based on our current knowledge and does not release the user from personal responsibility. The object conditions and product suitability must be checked professionally and appropriately. Take into account the information given in the Safety Data Sheet. We are happy to provide test samples for trials. Issue: 14 July 2022