

KD-CHECK SD-1

Wet Developer

Product Description

- Solvent-based wet developer
- Type-tested according to DIN EN ISO 3452-2 and 3452-6
- Form d and e according to DIN EN ISO 3452-2
- Approved according to AMS 2644 (listed on QPL-AMS 2644)
- Suitable for metals and non-metals (suitability for plastics must be checked beforehand)
- Application by means of aerosol cans or with painting equipment
- Fast drying
- Forms a fine and uniform layer of developer
- Excellent contrast to the penetrant

Product Specifications

- Application range: -30 °C to +50 °C
- Corrosive components (fluorine, chlorine + sulphur): each < 200 ppm according to DIN EN ISO 3452-2
- Corrosive components (fluorine, chlorine + sulphur): < 1 % each according to ASME Code
- 5 years minimum keeping time at room temperature

Approvals and Specification

- Low sulphur and halogen content according to DIN EN ISO 3452-2 and ASME Code, Section V, Article 6
- Type-tested according to DIN EN ISO 3452-2 and 3452-6
- QPL-AMS 2644 listed
- Approved according to AREVA NP TLV 9017
- ASTM E 165, ASTM E 1417

Your Benefits

- Fast drying
- White, uniform and high-contrast layer



Packaging

- 500 ml aerosol can (order no.: 9903.1)
- 5 l canister (order no.: 9903.5)
- 10 l canister (order no.: 9903.2)

KARL DEUTSCH Prüf- und Messgerätebau GmbH + Co KG · Otto-Hausmann-Ring 101 · 42115 Wuppertal · Germany
Phone +49 202 7192 0 · Fax +49 202 7192 123 · info@karldeutsch.de · www.karldeutsch.de

The Technical Data Sheet provides recommendations and possible examples. Obligations or liability cannot be derived therefrom. The information is based on our current knowledge and does not release the user from personal responsibility. The object conditions and product suitability must be checked professionally and appropriately. Take into account the information given in the Safety Data Sheet. We are happy to provide test samples for trials. Issue: 14 July 2022